



TYPE: **Lime 'n' Grey**

LIME 'N' GREY

Typical Analysis

	Typical BGC Range	AS 1316	Units
Mortar Compressive Strengths			
7 day	25.9 – 27.8	<i>Min. 10</i>	(MPa)
28 day	26.4 – 33.4	<i>Min. 15</i>	(MPa)
Vicat Setting Time			
Normal Consistency	-	-	(%)
Initial Set	105 -120	<i>Min. 75</i>	(minutes)
Final Set	150 195	<i>Max. 720</i>	(minutes)
Chemical Analysis			
SO ₃	2.6 – 2.6	<i>Max. 3.5</i>	(%)
Loss on Ignition	5.7 – 5.9	-	(%)

Note: Typical range is at 95% confidence level, individual results may be outside of this range.

Issue Date: 30 March 2023