



TYPE: **Lime 'n' Lite Coastal**

LIME 'N' LITE COASTAL

Typical Analysis

	Typical BGC Range	AS 1316	Units
Mortar Compressive Strengths			
7 day	24.6 – 25.3	<i>Min. 10</i>	(MPa)
28 day	29.9 – 32.0	<i>Min. 15</i>	(MPa)
Vicat Setting Time			
Normal Consistency	-	-	(%)
Initial Set	75 - 90	<i>Min. 75</i>	(minutes)
Final Set	135 – 150	<i>Max. 720</i>	(minutes)
Chemical Analysis			
SO ₃	3.0 – 3.0	<i>Max. 3.5</i>	(%)
Loss on Ignition	6.6 – 6.6	-	(%)

Note: Typical range is at 95% confidence level, individual results may be outside of this range.

Issue Date: 30 March 2023